



The Alsa Corporation

The Worlds Most Exotic Finishes



MC-101Q

MirraChrome

Non Catalyzed Mid-coat

Product Number

MC-101Q

Description

Non Catalyzed Mid-coat

Description

MirraChrome is a low solids Mid-coat designed to give a chrome like appearance.

Mixing Ratio

Ready to Spray

Application

1. Apply Alsa Jet Black Stylin Basecoats ASB-13
2. Apply Alsa Speed Clear SC-1230 Allow **the Speed Clear to dry for 7-10 days.** Once the Speed Clear has been allowed to dry for the recommended time wipe the surface with Isopropyl alcohol to pre clean the surface.
3. Apply 2 Dust coats at 25 psi with an Iwata LPH50 with a 1.0 Fluid tip, apply one coat after the other. Allow the MirraChrome to sit over night in a clean area.
4. Wipe with a soft lint-free cloth to remove any excess dust/overspray.
5. Clear with Alsa Speed Clear SC-1230.

Dry times at 77° F

Dust Free Immediately

Tack Free in immediately

Force Drying

Flash time @ 77° F Immediately

Allow 12 –24 hours before wet Clearcoating